

## TEST REPORT: 7191088977-CHM14-03-PGK

Date: 16 JUN 2014

Tel: +65 68851322 Fax: +65 67784301

Client's Ref:

Email: tai-hoe.lin@tuv-sud-psb.sg

**Note:** This report is issued subject to the Testing and Certification Regulations of the TÜV SÜD Group and the General Terms and Conditions of Business of TÜV SÜD PSB Pte Ltd. In addition, this report is governed by the terms set out within this report.



PSB Singapore

Choose certainty.  
Add value.

### SUBJECT

Humid Sulphur Dioxide Test on Screws

### CLIENT

EJOT Asia Pacific Pte Ltd  
32 Old Toh Tuck Road  
#04-05  
I.Biz Centre  
Singapore 597658

Attn: Mr Noel Yu

### SAMPLE SUBMISSION DATE

24 Feb 2014

### DATE TEST CONDUCTED

24 Mar to 11 Apr 2014

### DESCRIPTION OF SAMPLE

One sample of self drilling screws described as follows, was submitted by the above client:

Brand : "EJOT"  
Model : JT2-6-5.5X25 C1000  
Quantity : 5



Laboratory:  
TÜV SÜD PSB Pte. Ltd.  
No.1 Science Park Drive  
Singapore 118221

Phone : +65-6885 1333  
Fax : +65-6776 8670  
E-mail: testing@tuv-sud-psb.sg  
www.tuv-sud-psb.sg  
Co. Reg : 199002667R

Regional Head Office:  
TÜV SÜD Asia Pacific Pte. Ltd.  
3 Science Park Drive, #04-01/05  
The Franklin, Singapore 118223  
TÜV®



**METHOD OF TEST**

1. AS 3566.2 - 2002  
"Self-drilling screws for the building and construction industries –  
Part 2 : Corrosion resistance requirements"
2. DIN 50018 - 97  
"Testing in a saturated atmosphere in the presence of sulphur dioxide"

Test Conditions :

Gas type	: Sulphur dioxide, SO <sub>2</sub> (99.9% purity)
Concentration of SO <sub>2</sub>	: 0.67%v/v theoretical SO <sub>2</sub> concentration at beginning of each test cycle (KFW 2.0S)
Test cycle	: Phase 1 - 8 hours at 40±3°C, including pre-heating Phase 2 - 16 hours, including cooling in ventilated test chamber to room temperature (21 to 25°C)
Relative humidity	: Phase 1 - greater than 95% (condensing) Phase 2 - 55 to 75%
Total duration	: 15 cycles
Position of specimens	: Inclined 15° from vertical

Method of Assessment

- 1) AS/NZS 1580.481.1.9 - 1998  
"Paints and related materials – Methods of test  
Method 481.1.9 : Coatings – Exposed to weathering – Degree of blistering"
- 2) ISO 10289 – 1999  
"Methods for corrosion testing of metallic and other inorganic coatings on metallic substrates  
– Rating of test specimens and manufactured articles subjected to corrosion tests"



**RESULTS**

Test Conducted	"EJOT" JT2-6-5.5X25 C1000 Self Drilling Screws	AS 3566.2 – 2002 Class 3 Requirements
Condensing atmosphere in the presence of sulphur dioxide, 15 cycles	No rusting nor blistering of coating on all five tested screw heads	<u>Screw heads :</u> <ul style="list-style-type: none"><li>- Red rust shall not be over 5% of the significant areas</li><li>- No blistering of coating</li></ul>

Remarks : Test was conducted on five screws mounted in non-metallic fixture.

All five tested screws met AS 3566.2 : 2002 Class 3 requirements on resistance to condensing atmosphere containing sulphur dioxide.

**MS PECK GEOK KHOON**  
TECHNICAL EXECUTIVE

**MRS WONG-LIN TAI HOE**  
PRODUCT MANAGER  
COATINGS  
CHEMICAL & MATERIALS

"EJOT" JT2-6-5.5X25 C1000 Self Drilling Screws




Figure 1. Before Test



Figure 2. After 15 cycles of exposure in condensing atmosphere containing sulphur dioxide

# TEST REPORT: 7191088977-CHM14-03-PGK

16 JUN 2014



PSB Singapore

Please note that this Report is issued under the following terms :

1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
2. The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
3. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
4. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
5. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science Park Drive Singapore 118221.

July 2011

